



PRODUCT TESTING SERVICE

100 Clemson Research Blvd. Anderson, SC 29625 Tel (864) 646-TILE Fax (864) 646-2821

TCNA TEST REPORT NUMBER:

TCNA-550-14

PAGE: 1 OF 1

TEST REQUESTED BY:

Arto Brick California Pavers

TEST METHOD: ASTM C1026-13: "Standard Test Method for Measuring the Resistance of Ceramic and Glass Tile to Freeze-Thaw Cycling"

Informal Test Method Description: This test method describes the procedures and equipment required to test either glazed or unglazed ceramic or glass tiles for resistance to repeated cycles of freezing and thawing. Tile of any size or shape may be tested by this test method. A designated test load of tile specimens is saturated with water prior to being placed face-up in a metal water-filled container inside a freezer. The water level is adjusted such that the tile specimens are partially submerged. A thermocouple is inserted into the bottom of the metal container such that the water surrounding the thermocouple is the last location to freeze and thaw. Freezing is followed by a thawing cycle using water that flows over the test load. The number of freeze-thaw cycles is recorded and after 300 cycles, the test load is visually examined for damage and checked for total weight loss.

This summary is provided for the reader's convenience and is not a complete description of the method. See ASTM C1026 for all method details and information.

TEST SUBJECT MATERIAL:

Identified by client as: "Oleson Persian Blue (OPB 1-5)"
Approximate Size as Received: 3"x3"

TEST DATE:

10/28/2014 – 1/26/2015


TEST PROCEDURE:

- Sample Prep: Five (5) specimens were prepared and conditioned according to ASTM C1026, section 7.1.1.
- The specimens were then subjected to three hundred (300) cycles of freeze-thaw consisting of freezing the tiles in water to 27°F and then thawing the tiles in water to 40°F.

TEST RESULTS:

Specimen #	Initial Dry Wt. (g)	Final Dry Wt. (g)	Observations After 300 Cycles	Total Wt. Loss (%) (Shall be less than 0.5% per ASTM C1026)
1	178.86	178.76	No Damage	0.06%
2	169.65	169.61	No Damage	0.02%
3	169.59	169.52	No Damage	0.04%
4	170.49	170.48	No Damage	0.01%
5	171.36	171.34	No Damage	0.01%

COMMENTS: None


Katelyn Simpson
Laboratory Manager

1/29/2015

Testing Services: testing@tileusa.com Literature Orders: literature@tileusa.com Web Site: www.tileusa.com

This report is confidential and has been prepared for the exclusive use of the client. It is not an endorsement, approval, certification, or criticism of any product by TCNA. This report shall not be published in any form without prior written consent from TCNA